

**TRILITE® SM210**

Mixed Bed Resin for Pure Water Application

**TRILITE® SM210** is a ready-to-use and highly regenerated mixed bed resin for high purity water application.

**TRILITE® SM210** is mixed bed resins of each component of strong acid cation exchange resin and strong base anion exchange resin. Cation and anion resins are mixed to give a stoichiometric equivalent of cation and anion exchange capacity.

**TRILITE® SM210** is particularly suitable for use in the polishing of high purity water for specialty electronics applications, pharmaceutical, power plant and chemical manufacturing industry.

**Physical and Chemical Properties**

Physical Form	Translucent spherical beads	
Matrix	Styrene-DVB, Gel	
Components	SAC	SBA
Volumetric mixed ratio(%)	45	55
Functional Group	Sulfonic acid	Type 1 (Trimethylammonium)
Ionic Form	H <sup>+</sup>	OH <sup>-</sup>
Conversion rate	99.0% ↑	95.0% ↑
Total Capacity(eq/ℓ)	1.8 ↑	1.0 ↑
Moisture Retention(%)	50~56	62~70
Particle Size(mm)	0.3 ~ 1.2	
Uniformity Coefficient	1.6 ↓	
Whole Beads(%)	95 ↑	
Crush Strength(kgf/bead)	0.4 ↑	

**Treated Water Quality**

Feed water	Portable water, Conductivity 150μs/cm, SV36
Outlet quality	Minimum 15.0 MΩ·cm ( in 10 minutes)

**Recommended Operating Conditions**

Operating Temp(°C)	60	pH Range	0~14
Bed Depth(mm)	800	Service Flow Rate(m/h)	5~60

---

## Applications

---

It is mostly and widely used to get high purity water such as simple production of pure water from potable water, Laboratories, EDM machines and post RO or EDI mixed-bed.

---

All information contained in brochure is not absolute rather than relative one, created under the controlled environment by Samyang Corporation. Therefore, Samyang Corporation has no legal responsibility with respect to any and all information provided in brochure.

Samyang's TRILITE Ion exchange resins are produced based on the ISO 9001, ISO 14001 certification.

Samyang Corporation, 31 Jong-ro 33-gil, Jongno-gu, Seoul, Korea Tel: (82)2-740-7732~7, Fax: (82)2-740-7709



[www.samyangtrilite.com](http://www.samyangtrilite.com)