

TRILITE® KC-08

Strong Acid Cation Exchange Resin

Rev.2 Nov 2018

TRILITE® KC-08 Strong Acid Cation Exchange Resin is a Gel Type polydispersed resin. Because of its excellent ion removal capacity, high purity water can be produced economically. TRILITE® KC-08 is a standard cross-linkage product and it has outstanding mechanical and chemical stability, leading to low crush rate even after long-term use. TRILITE® KC-08 can be supplied by Na⁺ form but H⁺ form can be available depending on application and user's request.

Physical and Chemical Properties

Physical Form	Goldenrod translucent spherical beads	Matrix	Styrene-DVB, Gel
Functional Group	Sulfonic acid	Ionic Form	Na ⁺
Total Capacity(eq/ℓ)	2.00 ↑	Moisture Retention(%)	43~50
Shipping Density(g/ℓ)	830	Particle Density	1.29
Uniformity Coefficient	1.6 ↓	Particle Size(mm)	0.3~1.2
Whole Beads(%)	90 ↑	Swelling(Na ⁺ →H ⁺ , %)	8

Recommended Operating Conditions

Operating Temp(°C)	120	pH Range	0~14
Bed Depth(mm)	1000	Service Flow Rate(m/h)	5~50
Regeneration			
Regenerant	HCl, H ₂ SO ₄	Concentration(%)	HCl(4~10), H ₂ SO ₄ (1~4)
Level(g/ℓ)	40~150	Flow Rate(m/h)	4~20
Rinse Requirement(BV)	4~10		

Applications

TRILITE® KC-08 is widely used for water treatment like industrial softening and demineralization.

All information contained in brochure is not absolute rather than relative one, created under the controlled environment by Samyang Corporation. Therefore, Samyang Corporation has no legal responsibility with respect to any and all information provided in brochure.

Samyang's TRILITE Ion exchange resins are produced based on the ISO 9001, ISO 14001 certification.

Samyang Corporation, 31 Jong-ro 33-gil, Jongno-gu, Seoul, Korea Tel: (02)740-7732~7, Fax: (02)740-7140

